



Description

Two-component, colored, solvent-free polyurethane coat for rubber flooring system.

Application

- Ideal for industrial, troweled flooring, mosaics, cement surfaces, workshops, and storage facilities.
- Also suitable for light and medium circulation.
- Sealing layer on top of seamless rubber floorings.

Technical Data

Test	Result
Appearance	liquid
Colors	available colors
Density (Kg/m ³)	1.40 - 1.50
Viscosity (cps)	2000 – 4000 mPa.s at 25°C
Adhesive strength (N/mm ²)	>3
Final strength at 25°C	after 7 days
Temperature for the application and drying of the material	15 – 35°C

Packaging

(A+B) 15Kg metal bucket

Storage

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30 °C.

Consumption

2-2.3 kg/ m² for two layers.

Application Instructions

Substrate

The level, dry, clean, and free of cracks, undulations, and dust solid substrates must have in order to ensure proper adhesion. On dry surfaces without rising humidity issues

Preparation Work

Before beginning installation, the substrate's surface needs to be thoroughly cleaned with a brush. Before beginning installation, minor inclinations must be leveled\

Application

- The components A (resin) and B (hardener) were properly mixed and placed in separate containers with specific weight ratios.
- For 1-2 minutes, mixing should be done using a low revolution mixer (300-600 rpm).

- If required, thoroughly stir the mixture towards the sides and the bottom of the container to ensure that the hardener is evenly distributed.
- Using a flat trowel under pressure, the well-mixed mixture is applied to closely scrape off the material.
- Can be recoated without the need for priming in the first 48 hours following application provided the surface is clean and dry.
- Depending on the kind, level of absorption, and roughness of the underlay, consumption ranges from 2.0-2.3kg/m² for 2 layers.

Cleaning

Tools should be cleaned with solvent immediately after use

Health and Safety

- The application must take place in well-aired places using protective gloves
- Skin or eye contact must be avoided, otherwise wash carefully with soap and water.
- Do not dispose directly to water or soil. Bury in landfill in accordance with the local regulations.
- For further information, request material safety data sheet (MSDS) for the product