



### Description

two-component, solvent-free, polyurethane coating designed for flooring systems; line paint white.

### Application

Ideal for industrial, troweled flooring, mosaics, cement surfaces, workshops, and storage facilities. Also suitable for light and medium circulation. Sealing layer on top of seamless rubber floorings

### Technical Data

Test	Result
Appearance	liquid
Colors	available colors
Density (Kg/m <sup>3</sup> )	1.40 - 1.50
Final strength at 25°C	after 7 days
Temperature for the application and drying of the material	15 – 35°C
Viscosity (25°C)	2000 – 4000 maps at 25°C

### Packaging

(A+B) 30Kg metal bucket

A: 25.700 Kg

B: 4.300 Kg

### Storage

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30 °C.

### Consumption

0.15– 0.2 kg/ m2 for one layer

### Application Instructions

#### Substrate

The level, dry, clean, and free of cracks, undulations, and dust solid substrates must have in order to ensure proper adhesion. On dry surfaces without rising humidity issues

#### Preparation Work

Before beginning installation, the substrate's surface needs to be thoroughly cleaned with a brush. Before beginning installation, minor inclinations must be leveled\

#### Application

- The components A (resin) and B (hardener) were properly mixed and placed in separate containers with specific weight ratios. For 1-2 minutes, mixing should be done using a low revolution mixer (300-600 rpm). If required, thoroughly stir the mixture towards the sides and the bottom of the container to ensure that the hardener is evenly distributed.

- Using a flat trowel under pressure, the well-mixed mixture is applied to closely scrape off the material.
- Can be recoated without the need for priming in the first 48 hours following application provided the surface is clean and dry.
- Depending on the kind, level of absorption, and roughness of the underlay, consumption ranges from 2.0-2.3kg/m<sup>2</sup> for 2 layers.

### Cleaning

Tools should be cleaned with solvent immediately after use

### Health and Safety

- The application must take place in well-aired places using protective gloves
- Skin or eye contact must be avoided, otherwise wash carefully with soap and water.
- Do not dispose directly to water or soil. Bury in landfill in accordance with the local regulations.
- For further information, request material safety data sheet (MSDS) for the product